

Low odor MAH Grafted PP ST- 13LO

Product Profile

ST-13LO is a kind of maleic anhydride modified PP, the grafting rate is stable, low odor, and the appearance is white or light yellow particles.

Specification

Item	Unit	Value
Melt Index (190℃, 2.16kg)	g/10min	60-100
MAH Content	%	0.8-1.1

Application

It is used in the blending modification system of PP, so that PP and polar materials have good interfacial compatibility, improve the mechanical properties of materials, and reduce the exposure of glass fiber.

Recommended Dosage

1. In filled or reinforced PP, 3-8% is recommended.
2. In PA/PP alloy, 5-8% is recommended.

Package & Storage

25kg/package. Transported as common chemicals. Keep in dry, cool place. Storage temperature not exceeds 45℃.